



Product Name	Summarized Compositions	Gauges		Barrier Strength			Transmission Rate		Compatible Tray/Cup Substrates					Seal Type		Processes			Recommended Seal Temp. Range		
				Breathable	Standard	High	OTR (cc/100 sq. in)	WVTR (g/100 sq. in)	PET, A-PET, PET, PETG	PP	HDPE, PE-coated	PS, HIPS	PVC, PET-coated	Peelable (Easy, Medium, Hard)	Permanent / Weld	Microwaveable	HPP	Hot Fill	Anti-Fog	*F	*C
LOCK SEAL																					
TSPP110-35	OPP / AF-CPP	35µm	1.4mil	•			> 122.0	< 0.52		•					•	•		•	•	284 ~ 356	140 ~ 180
TSPE230-77	PET / LLDPE	77µm	3.0mil		•		< 8.4	< 0.52			•				•			•	•	302 ~ 356	150 ~ 180
TSPE221-67	PET / EVOH COEX	67µm	2.6mil			•	< 0.13	< 0.58			•				•			•	•	302 ~ 356	150 ~ 180
TSPP210-32	PET / AF-CPP	32µm	1.3mil		•		< 8.4	< 0.77		•					•	•		•	•	284 ~ 356	140 ~ 180
TSPP210-42	PET / CPP	42µm	1.7mil		•		< 8.4	< 0.65		•					•	•		•	•	302 ~ 374	150 ~ 190
TSPP310-32	KPET / AF-CPP	32µm	1.3mil			•	< 0.77	< 0.58		•					•	•		•	•	284 ~ 356	140 ~ 180
EASY PEEL																					
ESPP120-52	OPP / ESPP	52µm	2.0mil	•			> 116.1	< 0.52		•				E - M		•		•		284 ~ 320	140 ~ 160
ESPT120-52	OPP / ESPT	52µm	2.0mil	•			> 116.1	< 0.52	•	•	•	•	•	E - M		•				266 ~ 410	130 ~ 210
ESPP220-52	PET / ESPP	52µm	2.0mil		•		< 8.4	< 0.65		•				E - M		•		•		302 ~ 356	150 ~ 180
ESPP220-52 White	PET / ESPP	52µm	2.0mil		•		< 8.4	< 0.65		•				E - M		•		•		302 ~ 356	150 ~ 180
ESPT220-52	PET / ESPT	52µm	2.0mil		•		< 8.4	< 0.65	•	•	•	•	•	E - M		•				266 ~ 410	130 ~ 210
ESPT220-72	PET / ESPT	72µm	2.8mil		•		< 8.4	< 0.52	•	•	•	•	•	M - H		•	•			266 ~ 410	130 ~ 210
EXPT221-72	PET / HB EXPT	72µm	2.8mil			•	< 0.13	< 0.48	•	•	•	•	•	M - H		•	•			266 ~ 410	130 ~ 210
ESPP320-52	KPET / ESPP	52µm	2.0mil			•	< 0.77	< 0.58		•				E - M		•		•		302 ~ 356	150 ~ 180
ESPT320-52	KPET / ESPT	52µm	2.0mil			•	< 0.77	< 0.58	•	•	•	•	•	E - M		•				266 ~ 410	130 ~ 210

- Peel strength subject to machine settings & tray/cup compatibility
- Technical Service & Development for custom structures including retort applications
- Detailed specifications in individual technical data sheets, available by request
- Flexographic & rotogravure printing available with full graphics support